

SMT-2594

25%Cr-7%Ni-4.5%Mo-0.25%N Super Duplex STS

Conformances

AWS A5.9/ ASME SFA5.9 ER2594

EN ISO 14343-A G 25 9 4 NL

ABS AWS A5.9 ER2594

LR AWS A5.9 ER2594

DNV-GL Duplex Stainless Steels (-50°C)


Applications

- Offshore structure & FPSO, chemical and petrochemical plants

Features

- Excellent corrosion resistance
- Superior pitting resistance

Welding Position



Current

GMAW: DC + / GTAW: DC -

Shielding Gas

Ar / Ar+ O₂

Diameter / Packaging

Diameter mm (in)	Spool			Pac		
	12.5kg (28lbs)	15kg (33 lbs)	20kg (44lbs)	150kg (330lbs)	200kg (440lbs)	250kg (551lbs)
0.8 (0.033)	✓					
0.9 (0.035)	✓					
1.0 (0.040)	✓					
1.2 (0.045)	✓					
1.4 (0.052)						
1.6 (1/16)	✓					

Diameter mm (in)	5kg*1000						
	1.0 (0.039)	1.2 (0.045)	1.6 (1/16)	2.0 (5/64)	2.4 (3/32)	2.6 (0.10)	3.2 (1/8)
			✓	✓	✓	✓	✓

SMAW

SAW

GMAW

GTAW

FCAW

Non-FERROUS

APPENDIX

Typical Chemical Composition of the Wire(%)

C	Si	Mn	P	S	Cr	Ni	Mo	Cu	N
0.011	0.41	0.53	0.019	0.001	25.27	9.13	3.86	0.21	0.257

Typical Mechanical Properties of All-Weld Metal

TS MPa(lbs/in ²)	EL (%)	Temp °C(°F)	CVN-Impact Value J (ft.-lbs)	PREN
890 (129,000)	28.6	-50 (-58)	195 (144)	40

Typical Welding Parameters

Diameter, Polarity Shielding Gas	CTWD mm(in)	Wire Feed Speed m/min (in/min)	Amp. (A)	Volt. (V)	Deposition Rate kg/hr (lb/hr)
1.0mm (0.040 in), DC +					
100% Ar Gas	15~20 (0.59~0.78)	6.0 (236)	140	24	2.1 (4.6)
		7.1 (280)	160	24	2.5 (5.5)
		9.2 (362)	190	24	3.2 (7.1)
Mixed Gas (Ar + 2% O ₂)	15~20 (0.59~0.78)	5.2 (204)	160	26	1.8 (4.0)
		7.0 (276)	190	26	2.4 (5.3)
		8.3 (327)	220	26	2.9 (6.4)
1.2mm (0.045 in), DC +					
100% Ar Gas	15~20 (0.59~0.78)	9.2 (362)	190	27	4.6 (10.1)
		11.9 (469)	220	27	6.0 (13.2)
		15.5 (610)	260	27	7.8 (17.2)
Mixed Gas (Ar + 2% O ₂)	15~20 (0.59~0.78)	7.7 (303)	200	28	3.9 (8.6)
		8.6 (339)	230	28	4.3 (9.5)
		10.1 (398)	260	28	5.1 (11.2)